

Recommended Cutting Conditions

◆ GBA insert (Ground Chipbreaker)

Workpiece Material	Recommended Insert Grade (Cutting Speed: m/min)									① f at Grooving (mm/rev) ② f at Traversing (mm/rev) ③ // ap (mm)					Remarks
	Cermet		PVD Coated Carbide			Carbide	CBN	PCD							
	TC40	TN90	PR630	PR930	PR1115	PR905	KW10	KBN510 KBN525	KPD001 (KPD010)	GBA○○% 033~100	GBA○○% 125~200	GBA○○% 230~300	GBA○○% 330~400	GBA○○% 400~480	
Carbon Steel	☆ 150-220	☆ 150-220	☆ 80-200	☆ 80-180	★ 80-180	-	-	-	-	①0.03~0.08 ②Traversing N.A. ③Traversing N.A.	①0.04~0.09 ②0.04~0.09 ③Max. 0.3	①0.05~0.1 ②0.05~0.1 ③Max. 0.5	①0.05~0.12 ②0.05~0.1 ③Max. 0.5	①0.05~0.12 ②0.05~0.1 ③Max. 0.8	Coolant
Alloy Steel	☆ 130-200	☆ 130-200	☆ 80-180	☆ 80-160	★ 80-160	-	-	-	-	①0.03~0.07 ②Traversing N.A. ③Traversing N.A.	①0.04~0.08 ②0.04~0.08 ③Max. 0.3	①0.05~0.09 ②0.05~0.09 ③Max. 0.5	①0.05~0.1 ②0.05~0.1 ③Max. 0.5	①0.05~0.1 ②0.05~0.1 ③Max. 0.8	
Stainless Steel	-	☆ 70-150	☆ 60-150	☆ 60-130	★ 60-130	-	-	-	-	①0.03~0.07 ②Traversing N.A. ③Traversing N.A.	①0.04~0.08 ②0.04~0.08 ③Max. 0.3	①0.05~0.09 ②0.05~0.09 ③Max. 0.5	①0.05~0.1 ②0.05~0.1 ③Max. 0.5	①0.05~0.1 ②0.05~0.1 ③Max. 0.8	
Cast Iron	-	-	-	-	-	★ 80-180	☆ 60-120	★ 150-400	-	①0.03~0.08 ②Traversing N.A. ③Traversing N.A.	①0.04~0.09 ②0.04~0.09 ③Max. 0.3	①0.05~0.1 ②0.05~0.1 ③Max. 0.5	①0.05~0.12 ②0.05~0.1 ③Max. 0.5	①0.05~0.12 ②0.05~0.1 ③Max. 0.8	
Aluminum	-	-	-	-	-	-	★ 150-400	-	★ 150-2000	①0.05~0.12 ②Traversing N.A. ③Traversing N.A.	①0.05~0.15 ②0.05~0.15 ③Max. 0.5	①0.05~0.15 ②0.05~0.15 ③Max. 0.8	①0.08~0.15 ②0.08~0.15 ③Max. 0.8	①0.08~0.15 ②0.08~0.15 ③Max. 0.8	
Brass	-	-	-	-	-	-	★ 150-300	-	★ 200-800	①0.05~0.12 ②Traversing N.A. ③Traversing N.A.	①0.05~0.15 ②0.05~0.15 ③Max. 0.5	①0.05~0.15 ②0.05~0.15 ③Max. 0.8	①0.08~0.15 ②0.08~0.15 ③Max. 0.8	①0.08~0.15 ②0.08~0.15 ③Max. 0.8	
Hard Materials	-	-	-	-	-	-	-	★ 80-120	-	-	①0.02~0.05 ②Traversing N.A. ③Traversing N.A.	①0.03~0.07 ②0.01~0.04 ③Max. 0.1	-	-	

* Above cutting condition is for external grooving. Set both cutting speed and feed rate lower than 10% for internal grooving.

★ : 1st Recommendation ☆ : 2nd Recommendation

◆ GBA insert (MY Chipbreaker)

Workpiece Material	Recommended Insert Grade (Cutting Speed: m/min)								① f at Grooving (mm/rev) ② f at Traversing (mm/rev) ③ // ap (mm)					Remarks
	Cermet		PVD Coated Carbide			Carbide	CBN	PCD						
	TN6020	TC40	PR630	PR930	PR1115	KW10	KBN510	KPD001 (KPD010)	GBA43 ^R / _L 175MY~200MY	GBA43 ^R / _L 230MY~265MY	GBA43 ^R / _L 300MY	GBA43 ^R / _L 330MY ~350MY	GBA43 ^R / _L 400MY	
Carbon Steel	☆ 150-220	-	-	☆ 80-200	★ 80-200	-	-	-	①0.03~0.08 ②0.03~0.08 ③Max. 0.3	①0.04~0.09 ②0.04~0.09 ③Max. 0.3	①0.05~0.1 ②0.05~0.1 ③Max. 0.5	①0.05~0.12 ②0.05~0.1 ③Max. 0.5	①0.05~0.12 ②0.05~0.1 ③Max. 0.8	Coolant
Alloy Steel	☆ 130-200	-	-	☆ 80-180	★ 80-180	-	-	-	①0.03~0.07 ②0.03~0.1 ③Max. 0.3	①0.04~0.08 ②0.04~0.08 ③Max. 0.3	①0.05~0.09 ②0.05~0.09 ③Max. 0.5	①0.05~0.1 ②0.05~0.1 ③Max. 0.5	①0.05~0.1 ②0.05~0.1 ③Max. 0.8	
Stainless Steel	☆ 70-150	-	-	☆ 60-150	★ 60-150	-	-	-	①0.03~0.07 ②0.03~0.1 ③Max. 0.3	①0.04~0.08 ②0.04~0.08 ③Max. 0.3	①0.05~0.09 ②0.05~0.09 ③Max. 0.5	①0.05~0.1 ②0.05~0.1 ③Max. 0.5	①0.05~0.1 ②0.05~0.1 ③Max. 0.8	

* Above cutting condition is for external grooving. Set both cutting speed and feed rate lower than 10% for internal grooving.

★ : 1st Recommendation ☆ : 2nd Recommendation

◆ GB insert (Ground Chipbreaker)

➡ changes to GBA type.

Workpiece Material	Recommended Insert Grade (Cutting Speed: m/min)								① f at Grooving (mm/rev) ② f at Traversing (mm/rev) ③ // ap (mm)					Remarks
	Cermet			PVD Coated Carbide		Carbide	CBN	PCD						
	TN90	TC40	TC60	PR630	PR930	KW10	KBN510	KPD001 (KPD010)	GB○○% 050~100	GB○○% 125~200	GB○○% 230~300	GB○○% 330~400	GB○○% 400~480	
Carbon Steel	-	☆ 150-220	☆ 100-150	☆ 80-200	★ 80-180	-	-	-	①0.03~0.08 ②Traversing N.A. ③Traversing N.A.	①0.04~0.09 ②0.04~0.09 ③Max. 0.3	①0.05~0.1 ②0.05~0.1 ③Max. 0.5	①0.05~0.12 ②0.05~0.1 ③Max. 0.5	①0.05~0.12 ②0.05~0.1 ③Max. 0.8	Coolant
Alloy Steel	-	☆ 130-200	☆ 80-130	☆ 80-180	★ 80-160	-	-	-	①0.03~0.07 ②Traversing N.A. ③Traversing N.A.	①0.04~0.08 ②0.04~0.08 ③Max. 0.3	①0.05~0.09 ②0.05~0.09 ③Max. 0.5	①0.05~0.1 ②0.05~0.1 ③Max. 0.5	①0.05~0.1 ②0.05~0.1 ③Max. 0.8	
Stainless Steel	-	-	☆ 60-100	☆ 60-150	★ 60-130	-	-	-	①0.03~0.07 ②Traversing N.A. ③Traversing N.A.	①0.04~0.08 ②0.04~0.08 ③Max. 0.3	①0.05~0.09 ②0.05~0.09 ③Max. 0.5	①0.05~0.1 ②0.05~0.1 ③Max. 0.5	①0.05~0.1 ②0.05~0.1 ③Max. 0.8	
Cast Iron	-	-	-	-	-	★ 60-100	-	-	①0.03~0.08 ②Traversing N.A. ③Traversing N.A.	①0.04~0.09 ②0.04~0.09 ③Max. 0.3	①0.05~0.1 ②0.05~0.1 ③Max. 0.5	①0.05~0.12 ②0.05~0.1 ③Max. 0.5	①0.05~0.12 ②0.05~0.1 ③Max. 0.8	
Aluminum	-	-	-	-	-	★ 150-400	-	★ 150-2000	①0.05~0.12 ②Traversing N.A. ③Traversing N.A.	①0.05~0.15 ②0.05~0.15 ③Max. 0.5	①0.05~0.15 ②0.05~0.15 ③Max. 0.8	①0.08~0.15 ②0.08~0.15 ③Max. 0.8	①0.08~0.15 ②0.08~0.15 ③Max. 0.8	
Brass	-	-	-	-	-	★ 150-300	-	★ 200-800	①0.05~0.12 ②Traversing N.A. ③Traversing N.A.	①0.05~0.15 ②0.05~0.15 ③Max. 0.5	①0.05~0.15 ②0.05~0.15 ③Max. 0.8	①0.08~0.15 ②0.08~0.15 ③Max. 0.8	①0.08~0.15 ②0.08~0.15 ③Max. 0.8	

* Above cutting condition is for external grooving. Set both cutting speed and feed rate lower than 10% for internal grooving.

★ : 1st Recommendation ☆ : 2nd Recommendation

G

Grooving