

Recommended Cutting Conditions

Recommended Cutting Conditions - Boring (Positive Insert: Cutting Dia under 10mm) [ap indicates radius]

ISO Classification	Workpiece Material	Hardness	Cutting Range	Application	Recommended Chipbreaker	Recommended Grade	Corner R (rε)	Lower Limit - Recommendation - Upper Limit		
								Vc(m/min)	ap(mm)	f(mm/rev)
*P	Low-carbon Steel Low-carbon Alloy	HB ≧ 300	Finishing (Solid Type)	Continuous Interruption	(VNB)	PR930	0.03 0.2	30 - 60 - 100 30 - 60 - 80	0.05 - 0.08 - 0.1 0.05 - 0.1 - 0.15	0.03 - 0.05 - 0.07 0.03 - 0.07 - 0.1
			Finishing	Continuous Interruption	F, FSF	PR1025	0.1 0.2	30 - 60 - 100 30 - 60 - 80	0.05 - 0.08 - 0.1 0.05 - 0.1 - 0.15	0.03 - 0.05 - 0.07 0.03 - 0.07 - 0.1
			Finishing-Medium	Continuous Interruption	GQ	PR1025	0.2 0.4	30 - 60 - 100 30 - 60 - 80	0.1 - 0.2 - 0.3 0.1 - 0.2 - 0.3	0.03 - 0.05 - 0.07 0.03 - 0.07 - 0.1
	Medium-carbon Steel Medium-carbon Alloy	HB ≧ 300	Finishing (Solid Type)	Continuous Interruption	(VNB)	PR930	0.03 0.2	30 - 60 - 100 30 - 60 - 80	0.05 - 0.08 - 0.1 0.05 - 0.1 - 0.15	0.03 - 0.05 - 0.07 0.03 - 0.07 - 0.1
			Finishing	Continuous Interruption	F, FSF	PR1025	0.1 0.2	30 - 60 - 100 30 - 60 - 80	0.05 - 0.08 - 0.1 0.05 - 0.1 - 0.15	0.03 - 0.05 - 0.07 0.03 - 0.07 - 0.1
			Finishing-Medium cutting	Continuous Interruption	GQ	PR1025	0.2 0.4	30 - 60 - 100 30 - 60 - 80	0.1 - 0.2 - 0.3 0.1 - 0.2 - 0.3	0.03 - 0.05 - 0.07 0.03 - 0.07 - 0.1
	High-carbon Alloy	HB ≧ 280	Finishing (Solid Type)	Continuous Interruption	(VNB)	PR930	0.03 0.2	30 - 60 - 100 30 - 50 - 80	0.05 - 0.08 - 0.1 0.05 - 0.1 - 0.15	0.03 - 0.05 - 0.07 0.03 - 0.07 - 0.1
			Finishing	Continuous Interruption	F, FSF	PR1225	0.1 0.2	30 - 60 - 100 30 - 50 - 80	0.05 - 0.08 - 0.1 0.05 - 0.1 - 0.15	0.03 - 0.05 - 0.07 0.03 - 0.07 - 0.1
			Finishing-Medium	Continuous Interruption	GQ	PR1225	0.2 0.4	30 - 60 - 100 30 - 50 - 80	0.1 - 0.2 - 0.3 0.1 - 0.2 - 0.3	0.03 - 0.05 - 0.07 0.03 - 0.07 - 0.1
M	Stainless Steel	HB ≧ 220	Finishing (Solid Type)	Continuous Interruption	(VNB)	PR930	0.03 0.2	30 - 60 - 100 30 - 50 - 70	0.05 - 0.08 - 0.1 0.05 - 0.1 - 0.15	0.03 - 0.05 - 0.07 0.03 - 0.07 - 0.1
			Finishing	Continuous Interruption	F, FSF	PR1225	0.1 0.2	30 - 60 - 100 30 - 50 - 70	0.05 - 0.08 - 0.1 0.05 - 0.1 - 0.15	0.03 - 0.05 - 0.07 0.03 - 0.07 - 0.1
			Finishing-Medium	Continuous Interruption	GQ	PR1225	0.2 0.4	30 - 60 - 100 30 - 50 - 70	0.1 - 0.2 - 0.3 0.1 - 0.2 - 0.3	0.03 - 0.05 - 0.07 0.03 - 0.07 - 0.1
	Stainless Steel	HB ≧ 300	Finishing (Solid Type)	Continuous Interruption	(VNB)	PR930	0.03 0.2	30 - 60 - 80 20 - 40 - 60	0.05 - 0.08 - 0.1 0.05 - 0.1 - 0.15	0.03 - 0.05 - 0.07 0.03 - 0.07 - 0.1
			Finishing	Continuous Interruption	F, FSF	PR1225	0.1 0.2	30 - 60 - 80 20 - 40 - 60	0.05 - 0.08 - 0.1 0.05 - 0.1 - 0.15	0.03 - 0.05 - 0.07 0.03 - 0.07 - 0.1
			Finishing-Medium	Continuous Interruption	GQ	PR1225	0.2 0.4	30 - 60 - 80 20 - 40 - 60	0.1 - 0.2 - 0.3 0.1 - 0.2 - 0.3	0.03 - 0.05 - 0.07 0.03 - 0.07 - 0.1
K	Gray Cast Iron	HB ≧ 250	Finishing (Solid Type)	Continuous Interruption	(VNB) (VNB-NB)	KW10	0.03 0.2	30 - 60 - 100 30 - 60 - 100	0.05 - 0.08 - 0.1 0.05 - 0.1 - 0.15	0.03 - 0.05 - 0.07 0.03 - 0.07 - 0.1
			Finishing	Continuous Interruption	F	KW10	0.1 0.2	30 - 60 - 100 30 - 60 - 80	0.05 - 0.08 - 0.1 0.05 - 0.1 - 0.15	0.03 - 0.05 - 0.07 0.03 - 0.07 - 0.1
			Finishing-Medium	Continuous Interruption	HQ	CA4505 CA4515	0.2 0.4	30 - 60 - 100 30 - 60 - 80	0.1 - 0.2 - 0.3 0.1 - 0.2 - 0.3	0.03 - 0.05 - 0.07 0.03 - 0.07 - 0.1
	Nodular Cast Iron	HB ≧ 270	Finishing (Solid Type)	Continuous Interruption	(VNB) (VNB-NB)	KW10	0.03 0.2	30 - 60 - 80 30 - 60 - 80	0.05 - 0.08 - 0.1 0.05 - 0.1 - 0.15	0.03 - 0.05 - 0.07 0.03 - 0.07 - 0.1
			Finishing	Continuous Interruption	F, U	KW10	0.1 0.2	30 - 60 - 80 30 - 60 - 80	0.05 - 0.08 - 0.1 0.05 - 0.1 - 0.15	0.03 - 0.05 - 0.07 0.03 - 0.07 - 0.1
			Finishing-Medium	Continuous Interruption	Standard	CA4505 CA4515	0.2 0.4	30 - 60 - 100 30 - 60 - 80	0.1 - 0.2 - 0.3 0.1 - 0.2 - 0.3	0.03 - 0.05 - 0.07 0.03 - 0.07 - 0.1
N	Non-ferrous Metals	HB ≧ 100	High Speed Cutting (Rainbow Surface Gross)	Continuous	Without Chipbreaker	KPD001	0.05	150 - 200 - 300	0.05 - 0.1 - 0.3	0.05 - 0.1 - 0.15
			Finishing	Continuous Interruption	F, U	KW10	0.1 0.2	100 - 150 - 200 100 - 150 - 200	0.05 - 0.3 - 0.5 0.05 - 0.3 - 0.5	0.03 - 0.1 - 0.2 0.03 - 0.1 - 0.2
S	Titanium Alloy	HB ≧ 400	Precision Cutting (Rainbow Surface Gross)	Continuous Interruption	Without Chipbreaker	KPD001	0.1 0.2	100 - 120 - 150 70 - 100 - 120	0.05 - 0.1 - 0.3 0.05 - 0.1 - 0.3	0.03 - 0.07 - 0.1 0.03 - 0.07 - 0.1
			Finishing	Continuous Interruption	F, U	KW10	0.1 0.2	20 - 40 - 60 20 - 40 - 60	0.05 - 0.2 - 0.5 0.05 - 0.2 - 0.5	0.03 - 0.1 - 0.2 0.03 - 0.1 - 0.2
	Heat-resistant Alloys	HB ≧ 350	Finishing (Solid Type)	Continuous Interruption	(VNB)	KW10	0.2 0.2	10 - 30 - 50 10 - 30 - 50	0.05 - 0.1 - 0.3 0.05 - 0.1 - 0.3	0.03 - 0.05 - 0.1 0.03 - 0.05 - 0.08
			Finishing	Continuous Interruption	F, U	KW10	0.2 0.2	10 - 30 - 50 10 - 30 - 50	0.05 - 0.2 - 0.4 0.05 - 0.2 - 0.4	0.03 - 0.05 - 0.1 0.03 - 0.05 - 0.1
H	Hard Materials	40~50 HRC	Finishing	Continuous Interruption	(VNB)	PR930	0.2 0.2	30 - 50 - 70 30 - 50 - 70	0.05 - 0.1 - 0.4 0.05 - 0.1 - 0.2	0.01 - 0.02 - 0.05 0.01 - 0.02 - 0.03
		45~68 HRC	Finishing	Continuous Interruption	SE SET	KBN25M	0.2 0.4	60 - 100 - 120 60 - 80 - 100	0.05 - 0.1 - 0.2 0.05 - 0.1 - 0.2	0.02 - 0.05 - 0.1 0.02 - 0.05 - 0.1

* Please use it with PR1005 set to Vc=150m/min or below, for machining of free-cutting steel such as small size 11SMn (SUM). For ap and feed, see low carbon steel.