

Recommended Cutting Conditions

Workpiece Material		Hardness (HB)	Cutting conditions		Cutting Dia ϕD_c (mm)							Remarks	
			Cutting Speed V_c (m/min)	Spindle Revolution n (min ⁻¹) Feed Rate f (mm/rev)	$\phi 8$	$\phi 10$	$\phi 12$	$\phi 14$	$\phi 16$	$\phi 18$	$\phi 20$		$\phi 25$
Low-carbon Steel	SS400 S10C~S25C	125	120 - 180	n (min ⁻¹)	4,780 - 7,170	3,820 - 5,730	3,180 - 4,780	2,730 - 4,090	2,390 - 3,580	2,120 - 3,180	1,910 - 2,870	1,530 - 2,290	
				f (mm/rev)	0.11 - 0.20	0.13 - 0.24	0.14 - 0.28	0.17 - 0.32	0.19 - 0.35	0.23 - 0.38	0.25 - 0.41	0.30 - 0.50	
Carbon Steel	S30C~S58C (Annealed)	190	100 - 150	n (min ⁻¹)	3,980 - 5,970	3,180 - 4,780	2,650 - 3,980	2,270 - 3,410	1,990 - 2,990	1,770 - 2,650	1,590 - 2,390	1,270 - 1,910	
				f (mm/rev)	0.13 - 0.24	0.15 - 0.29	0.17 - 0.33	0.19 - 0.36	0.22 - 0.41	0.25 - 0.46	0.28 - 0.48	0.32 - 0.60	
	S30C~S58C (Heat treated)	250	80 - 120	n (min ⁻¹)	3,180 - 4,780	2,550 - 3,820	2,120 - 3,180	1,820 - 2,730	1,590 - 2,390	1,420 - 2,120	1,270 - 1,910	1,020 - 1,530	
				f (mm/rev)	0.13 - 0.21	0.15 - 0.25	0.18 - 0.31	0.21 - 0.39	0.23 - 0.45	0.25 - 0.53	0.28 - 0.61	0.38 - 0.64	
		300	50 - 75	n (min ⁻¹)	1,990 - 2,990	1,590 - 2,390	1,330 - 1,990	1,140 - 1,710	1,000 - 1,490	880 - 1,330	800 - 1,190	640 - 960	
				f (mm/rev)	0.11 - 0.19	0.12 - 0.23	0.16 - 0.28	0.21 - 0.32	0.23 - 0.35	0.25 - 0.41	0.28 - 0.41	0.32 - 0.45	
Alloy Steel	SCM, SCr etc. (Annealed)	180	70 - 95	n (min ⁻¹)	2,790 - 3,780	2,230 - 3,030	1,860 - 2,520	1,590 - 2,160	1,390 - 1,890	1,240 - 1,680	1,110 - 1,510	890 - 1,210	
				f (mm/rev)	0.15 - 0.28	0.16 - 0.35	0.21 - 0.37	0.23 - 0.46	0.25 - 0.46	0.25 - 0.51	0.30 - 0.51	0.35 - 0.60	
			275	70 - 95	n (min ⁻¹)	2,790 - 3,780	2,230 - 3,030	1,860 - 2,520	1,590 - 2,160	1,390 - 1,890	1,240 - 1,680	1,110 - 1,510	890 - 1,210
					f (mm/rev)	0.11 - 0.21	0.14 - 0.25	0.19 - 0.30	0.21 - 0.33	0.23 - 0.37	0.28 - 0.43	0.28 - 0.46	0.32 - 0.58
			300	60 - 90	n (min ⁻¹)	2,390 - 3,580	1,910 - 2,870	1,590 - 2,390	1,360 - 2,050	1,190 - 1,790	1,060 - 1,590	960 - 1,430	760 - 1,150
					f (mm/rev)	0.11 - 0.19	0.12 - 0.23	0.16 - 0.26	0.18 - 0.31	0.21 - 0.33	0.23 - 0.36	0.25 - 0.38	0.30 - 0.50
		350	50 - 75	n (min ⁻¹)	1,990 - 2,990	1,590 - 2,390	1,330 - 1,990	1,140 - 1,710	1,000 - 1,490	880 - 1,330	800 - 1,190	640 - 960	
				f (mm/rev)	0.11 - 0.20	0.12 - 0.23	0.16 - 0.25	0.17 - 0.29	0.18 - 0.32	0.20 - 0.36	0.23 - 0.38	0.28 - 0.50	
Stainless Steel	SUS304 SUS316	220	60 - 80	n (min ⁻¹)	2,390 - 3,180	1,910 - 2,550	1,590 - 2,120	1,360 - 1,820	1,190 - 1,590	1,060 - 1,420	960 - 1,270	760 - 1,020	
				f (mm/rev)	0.11 - 0.19	0.12 - 0.23	0.16 - 0.26	0.18 - 0.31	0.21 - 0.33	0.23 - 0.36	0.25 - 0.38	0.28 - 0.42	
	SUS630	300	50 - 70	n (min ⁻¹)	1,990 - 2,790	1,590 - 2,230	1,330 - 1,860	1,140 - 1,590	1,000 - 1,390	880 - 1,240	800 - 1,110	640 - 890	
				f (mm/rev)	0.11 - 0.20	0.12 - 0.23	0.16 - 0.25	0.17 - 0.29	0.18 - 0.32	0.20 - 0.36	0.23 - 0.38	0.25 - 0.40	
Gray Cast Iron	FC150~FC200	180	120 - 170	n (min ⁻¹)	4,780 - 6,770	3,820 - 5,410	3,180 - 4,510	2,730 - 3,870	2,390 - 3,380	2,120 - 3,010	1,910 - 2,710	1,530 - 2,170	
				f (mm/rev)	0.17 - 0.32	0.20 - 0.37	0.23 - 0.43	0.27 - 0.48	0.30 - 0.55	0.33 - 0.61	0.33 - 0.61	0.40 - 0.74	
	FC250~FC350	260	90 - 120	n (min ⁻¹)	3,580 - 4,780	2,870 - 3,820	2,390 - 3,180	2,050 - 2,730	1,790 - 2,390	1,590 - 2,120	1,430 - 1,910	1,150 - 1,530	
				f (mm/rev)	0.14 - 0.25	0.16 - 0.31	0.19 - 0.35	0.23 - 0.42	0.26 - 0.47	0.28 - 0.53	0.30 - 0.58	0.36 - 0.70	
Nodular Cast Iron	FCD400~FCD500	160	60 - 90	n (min ⁻¹)	2,390 - 3,580	1,910 - 2,870	1,590 - 2,390	1,360 - 2,050	1,190 - 1,790	1,060 - 1,590	960 - 1,430	760 - 1,150	
				f (mm/rev)	0.14 - 0.25	0.16 - 0.30	0.19 - 0.35	0.22 - 0.40	0.24 - 0.45	0.28 - 0.51	0.28 - 0.56	0.34 - 0.67	
	FCD600~FCD800	250	40 - 65	n (min ⁻¹)	1,590 - 2,590	1,270 - 2,070	1,060 - 1,730	910 - 1,480	800 - 1,290	710 - 1,150	640 - 1,040	510 - 830	
				f (mm/rev)	0.10 - 0.19	0.12 - 0.22	0.14 - 0.25	0.16 - 0.31	0.19 - 0.35	0.23 - 0.51	0.25 - 0.53	0.30 - 0.60	


Coolant (See K17)

- Internal coolant is recommended. In case of external coolant, cutting depth must be 3xD or less.
- The longer drilling depth gets (3D → 5D → 8D), the lower of the recommended feed rate should be set for f.

Reference charts

<Cutting conditions> : Workpiece Material Heat treated steel (Hardness 240HB) $V_c=80$ m/min, Wet

● Power requirement



● Torque

